

ITEM

LN-PT-0802 Version: A2

Date: May 21,2022

SBM 55 (RP-55)

SBM 55 is a heat stabilizer for polyvinyl chloride or other vinyl polymers and copolymers. SBM 55 is a mixture of beta-diketones. Since SBM 55 is thermally stable and harmless, it is an ideal stabilizer for using in food containers field.

SPECIFICATION

Appearance:	White to pale yellow powder
Melting Point:	53 °C Min.
Odor:	Slight
Assay:	190meq/100g Min.
Ashes:	0.2% Max.
Volatiles:	0.2% Max.
Loss on drying:	2.0% Max
Packing:	25 KGS / BAG 500 KGS / PALLET
Application:	SBM 55 is recommended as stabilizer for vinyl

Notice: Above information is based on our own investigation and experience, we do not assume any responsibility for the performance or result obtained through the use of our product. The users need to check the quality, safety and all properties in their side before they use and commercialize their products. Neither Longchem nor our agents shall take any responsibilities for any injury, loss or damages directly or indirectly caused by our products.

J.Y.C. GROUP LTD.

NO.46, Dou-kung 2 Rd, Dou-Liu City, Yun-Lin Hsien, 64069 Taiwan, R.O.C.

Tel: 886-5-5574403 Fax: 886-5-5574099

compounds to be used for manufacturing foodstuff containers or medical or pharmaceutical articles e.g. bottles, rigid sheet and films plastic zed films etc.